PREP P

SURFACE PREPARATION

KEY BENEFITS

- Pre-treatment for (teak)wood
- Enhances adhesion on porous substrates
- Fast Drying

PRODUCT DESCRIPTION

Bostik Prep P is a pre-treatment designed to improve the adhesion of most Bostik elastic bonding products on porous surface substrates.

APPLICATIONS

- Pre-treatment of mineral substrates (i.e. brickwork, concrete)
- Pre-treatment of wood substrates (i.e. seams in teak decks)

METHOD OF USE

Substrates should be clean, dry, dust- and grease-free. Prep P container should be kept closed until the moment of use. Do not use Prep P directly from the original container but pour as much Prep P into a clean glass or metal container as can be used within 30 minutes and immediately close the original container firmly.
Do not return unused material to the original container If necessary e.g. if heavily contaminated, substrates may first be cleaned with Cleaner I or Cleaner 14, allow cleaners to dry for 5 minutes before application of Prep P.
Apply Prep P in a thin layer to the surface for it to form a continuous, uninterrupted film. Do not apply Prep P on on already dried Prep P.
Best results are obtained when the bonding/sealing is realised within 6 hours after application of Prep P. Avoid contact with the cleaned, pre-treated surface, as this can lead to poor adhesion. Do not use when condensation is formed on the substrate.

TECHNICAL DATA

Specific Gravity	[g/ml]	ca. 1.1
Coverage	[m²/L]	8 - 10
Color		Light yellow/Transparent
Physical Form		Low viscous liquid
Dry Content	[%]	ca. 50
Drying Time [20°C/50%RH]	[min]	ca. 30
Flash Point closed cup	[°C]	ca. -4
Application Temperature	[°C]	+5 to +30

PACKAGING DESCRIPTION

500ml can

STORAGE STABILITY

Prep P can be stored for up to 12 months in unopened container in a dry area at temperatures between +5°C and +30°C. Once opened, Prep P can be used for a maximum of 2 weeks (container should be firmly closed when not in use).

FURTHER INFORMATION

The following publication is available on request:
- Material Safety Data Sheets (MSDS).

DISCLAIMER

Bostik provides this Technical Data Sheet (“TDS”) for descriptive and informational purposes only. It does not constitute a warranty, a contract, or a substitute for expert or professional advice. Please refer to the local product Safety Data Sheet for health and safety information. The statements, technical information, data, and recommendations contained in this TDS are provided “AS IS” without any warranties or guarantees of any kind. They represent typical results for the products based solely on Bostik’s research. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability for any damages of any kind that may result from the

use of the products, the results obtained, or reliance on the information contained herein.

Bostik SA
51, Esplanade du Général de Gaulle,
92800 Puteaux – France
Smart help: +33 149 007 502
www.bostik.com

All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.

PREP P – MDM-53504-01-WW – 2026, 31 October